



# Slags in ferroalloys production—review of present knowledge

by L. Holappa\* and Y. Xiao†

## Synopsis

Ferroalloys like FeCr and FeMn are mostly produced in submerged electric arc furnaces. Typical of these processes is that the amount of slag is quite high. The role of slag for the process is thus essential and specific chemical, physical and electrical properties are required. Slags in FeCr process are  $\text{Al}_2\text{O}_3$ -MgO-SiO<sub>2</sub> based with minor contents of CaO and CrO<sub>x</sub>. Slags in the FeMn process are principally similar, originating from silicate minerals but can have quite large composition range depending on the manganese ore and its gangue minerals. Characteristic of the FeMn process is that the slag is rich in manganese oxide up to above 30%. A common feature is that the 'ore oxides', CrO<sub>x</sub> and MnO<sub>x</sub> in slag are not only divalent oxides but also contain some higher valent of Cr<sup>3+</sup> and Mn<sup>3+</sup>, respectively. In FeMn production conditions the slag consists mainly of Mn<sup>2+</sup>. This is a clear difference from CrO<sub>x</sub> containing slags in which both two and three valent coexist in slags in FeCr process conditions. Oxidation state of the slag depends on the ambient oxygen partial pressure and temperature in the examined process. The thermodynamics of slags in ferroalloys, production are discussed in terms of phase diagrams, activities and oxidation state of chromium and manganese oxides. Further, slag properties influencing reduction kinetics and furnace operation i.e. viscosity and electrical resistivity are discussed.

**Keywords:** review, slags, ferroalloys, ferrochromium, ferromanganese, thermodynamics, physical properties

## Introduction

Stainless steel consumption is steadily growing 5 per cent per year on average, thus increasing production of ferrochrome. FeCr production (HC FeCr, 52 per cent Cr) has now reached the level of 5 Mton/year<sup>1</sup>. Production of Mn alloys, FeMn and SiMn, exceeds 6 Mton/year contributing to manganese content of 4–4.5 Mton/year but is growing slowly following the trend of global steel production which is increasing in long-term, although highly fluctuating, around 1–2 per cent/year. Manganese and silicon bearing ferroalloys (FeMn, FeSi, SiMn) are typical additives used in carbon steels as well as in low and high alloyed steels. In addition, 'minor alloys' (FeNi, FeMo, FeW, etc.) and microalloys (FeV, FeTi, FeNb, FeB, FeAl) are produced and used to make different steel grades with desired

properties. As the processes for these alloys are quite diverse and specific they are not discussed here. Considering silicon alloys slag properties is essential in refining processes, but in FeSi production the basic idea is just to reduce pure SiO<sub>2</sub> in a submerged-arc furnace. Consequently, the focus of this article is on slags of FeCr and FeMn processes.

Submerged-arc furnaces are used to smelt chromite and manganese ores into, respectively, ferrochrome and ferromanganese (containing silicon and carbon) as well as associated slags by the use of a suitable carbonaceous reductant (coke, anthracite, char). The slag is created in the process from gangue material associated with the ores as well as from fluxes added to the burden. The fluxes are added to assist in the smelting by affecting the activities of the oxides in the slag, melting temperatures of the slag, and its viscosity and electrical conductivity. Slags in the FeCr process are  $\text{Al}_2\text{O}_3$ -MgO-SiO<sub>2</sub> based with minor contents of CaO and CrO<sub>x</sub>. Slags in the FeMn process are principally similar, originating from silicate minerals, but can have quite large composition ranges depending on the manganese ore and its gangue minerals. Chromium content of FeCr slags is typically 5 to 10 of which a significant part is as metallic particles dispersed in the slag. Characteristic of FeMn processes is that the slag is rich in manganese oxide, up to above 30%. A common feature is that both Cr and Mn are present in two different valent states under process conditions, namely Cr<sup>2+</sup>/Cr<sup>3+</sup> and Mn<sup>2+</sup>/Mn<sup>3+</sup>, respectively. The oxidation state of chromium and manganese depends on the local oxygen partial pressure and temperature of the slags.

\* Helsinki University of Technology, Finland.

† Delft University of Technology, Netherlands.

© The South African Institute of Mining and Metallurgy, 2004. SA ISSN 0038-223X/3.00 + 0.00. The paper was presented at the SAIMM Conference: VII International Conference on Molten Slags Fluxes and Salts, 25–28 January 2004.

# Slags in ferroalloys production—review of present knowledge

A successful operation to a large extent depends on the metal recovery. For example, high chromium recovery would be beneficial in saving raw materials and energy as well as in reducing eventual chromium pollution from chromium containing slag and wastes. The knowledge of the thermodynamic properties of slags, including activities and phase relations, will definitely help to evaluate the equilibrium distribution, to promote process modelling, and further to better understand the process of achieving a higher recovery of metal from the slags.

Even though many papers have been published on chromium and manganese properties of metallurgical slags, some fundamental nature and behaviour in general still need to be clarified. In this paper, the available information on the oxide activities and the phase relations in the slag, the metal recovery, and some other properties such as viscosity and electrical conductivity are summarized and discussed. The aim is to provide a guided metallurgical knowledge and further to establish practical implications for the process operation and control of ferroalloy production.

## Thermodynamic properties of chromium bearing slags

A quantitative evaluation of the thermodynamic properties and roles of chromium oxides in silicate melts, and hence of the chromium distributions between slag and alloys, requires a knowledge of the activity-composition relations of chromium oxides as well as the phase relations in the slag. Chromium oxide containing slags have been investigated at temperatures corresponding to FeCr and stainless steel processes under different oxygen partial pressures ranging from a very strong reducing atmosphere to ambient air.

### Chromium–oxygen system

In order to understand the complexity of chromium containing slags, it is useful to examine the basic diagram of the Cr–O system, as shown in Figure 12. At low temperatures Cr has stable oxides of which the most common is Cr<sub>2</sub>O<sub>3</sub> (Cr<sup>3+</sup>) but oxides with higher oxidation state (Cr<sup>6+</sup>) can form under high oxygen partial pressure. Lower valent oxides are stable only at high temperatures, Cr<sub>3</sub>O<sub>4</sub> exists above 1650°C and divalent oxide CrO forms above 1665°C. When cooling down, it disproportionates to metallic Cr and Cr<sub>2</sub>O<sub>3</sub>:



As seen in Figure 1, liquid 'CrO' is formed at low oxygen partial pressure e.g. in equilibrium with metallic chromium or ferrochrome. It has a rather wide non-stoichiometric composition range. The oxygen partial pressure at the eutectic point is inferred to be of the order of 10<sup>-12</sup> atm<sup>2</sup>.

### Activities of chromium oxides in slag

The available activity data in the literature are still very limited, especially for the slag systems under the conditions for FeCr production. In most cases the slags were equilibrated with Cr metal or Cr alloy, only in a few cases was the ambient P<sub>O2</sub> controlled by the gas phase only. Xiao and Holappa<sup>3-5</sup> studied chromium containing slags equilibrated with metallic chromium crucible at 1500–1600°C. The oxidation state of chromium in CaO–SiO<sub>2</sub>–CrO<sub>x</sub> based slag was evaluated by the

wet chemical method, and activities of CrO and CrO<sub>1.5</sub> were determined by the electromotive force method. The effects of temperature, slag basicity, as well as additions of MgO and Al<sub>2</sub>O<sub>3</sub> were investigated. The divalent chromium fraction increased but the activities of chromium oxides decreased with temperature. The higher the slag basicity, the higher the activities of chromium oxides.

Figure 2 shows that the divalent chromium fraction in the slag decreases with increasing basicity and total CrO<sub>x</sub>. The index of *x* changes from a value slightly above 1.0 to a value almost 1.5. By partially substituting MgO for CaO, the activities of CrO and CrO<sub>1.5</sub> decreased, the oxidation state of chromium in the slag did not change significantly. Increasing Al<sub>2</sub>O<sub>3</sub> content to 10 mol% resulted in a lower divalent chromium fraction and higher activities of chromium oxides. A further increase in the Al<sub>2</sub>O<sub>3</sub> content to 20 mol% did not cause obvious change.

The CaO–SiO<sub>2</sub>–MgO–Al<sub>2</sub>O<sub>3</sub>–CrO<sub>x</sub> slags with a low melting point in relation to FeCr production were also investigated. The basic composition of the Cr-free slag was: (CaO) = 10 mol%, (SiO<sub>2</sub>) = 40 mol%, (MgO) = 35 mol% and (Al<sub>2</sub>O<sub>3</sub>) = 15 mol%. The CrO<sub>x</sub> varied from about 7.5 mol% to saturation. The results of the activities of the chromium oxides are presented in Figure 3. It can be seen that the solubility of CrO<sub>x</sub> in the slag is about 60 mol%, if the slag is in equilibrium with metallic chromium. In this slag system, the slag is more acidic, the slag basicity is less than 1.0, and the effect of MgO and Al<sub>2</sub>O<sub>3</sub> co-existence is incorporated.




Figure 1—Equilibrium relations in the Cr–Cr<sub>2</sub>O<sub>3</sub> system<sup>2</sup>




Figure 2—Oxidation state of chromium in the CaO–SiO<sub>2</sub>–CrO<sub>x</sub> slag system in equilibrium with metallic chromium<sup>5</sup>

## Slags in ferroalloys production—review of present knowledge




Figure 3—Activity of CrO and oxidation state of chromium in CaO-SiO<sub>2</sub>-MgO-Al<sub>2</sub>O<sub>3</sub>-CrO<sub>x</sub> slag at 1873 K in equilibrium with metallic chromium; standard state—pure liquid CrO




Figure 4—The effect of oxygen partial pressure on the oxidation state of chromium in slag from different researchers

In general, in silicate slags in equilibrium with Fe-Cr-O (unsaturated) melts or in silica saturated slag systems under low oxygen partial pressure, both Cr<sup>2+</sup> and Cr<sup>3+</sup> are present in all slags, and an equilibrium exists between these two valences, depending on the equilibrium oxygen partial pressure, slag composition and temperature. It was found that the ratio of Cr<sup>2+</sup>/Cr<sup>3+</sup> in the slag increased with higher temperature, lower oxygen partial pressure and lower slag basicity. In order to compare the available data in literature, some of the experimental results from different researchers were selected and compared under specific conditions in Figure 4. Due to the difference in experimental methods, conditions, as well as the slag analysing methods, there seems to exist a great discrepancy in the oxidation state of chromium in the slag.

Figure 5 shows a comparison of the activities of CrO. A general consistency of the activity values can be observed from the figure. The agreed conclusion is that increasing the slag basicity will increase the activity of chromium oxides. Also, temperature has a weak lowering effect on the activity of CrO. The activity coefficients of CrO and CrO<sub>1.5</sub> increased with increasing oxygen partial pressure and CaO content in the melts.

### Phase diagrams of slag systems containing chromium oxides

More than 35 phase relation diagrams were available to demonstrate the thermodynamic properties of chromium containing oxides systems. It seems that the phase relations of the metallurgical chromium oxide systems have been broadly investigated from the monometric Cr-O system to multicomponent oxide systems of Fe, Cr, Ca, Mg, Al and Si. The monometric, binary and ternary systems were investigated systematically, mainly in air atmosphere, and a few systems were studied in equilibrium with metallic chromium. An important system concerning FeCr production is the quasi-ternary MgO-SiO<sub>2</sub>-CrO<sub>x</sub>. The diagrams in air and in equilibrium with metallic Cr were presented in *Slag Atlas*<sup>15</sup>. The diagram of the system in equilibrium with metallic Cr shows the low liquidus area at lower slag basicity (SiO<sub>2</sub> around 60%) than the corresponding system with CaO. Both diagrams were given as ternaries with Cr<sub>2</sub>O<sub>3</sub> which is, evidently, not relevant for the Cr metal equilibrium, due to the significant amount of CrO in slag.

As to the quaternary chromium containing oxide systems, only the Ca-Mg-Si-Cr-O system was reported in the

# Slags in ferroalloys production—review of present knowledge




Figure 5—Comparison of  $a_{CrO}$  in silicate slag from different researchers

literature<sup>16</sup>. The quinary Ca-Mg-Al-Si-Cr-O system was only studied in air atmosphere, and the chromite spinel phase was the primary interest<sup>17</sup>. Based on the information above, the most important features of the liquidus surface of chromium oxide containing silicate systems are the larger liquid miscibility gaps and the dominance of the chromite spinel stability area. Subsolidus relations of special interest are those involving spinel phases. The oxygen potential of the gas phase is an important parameter in chromium oxide containing systems, as the oxidation state of chromium has a powerful influence on phase diagrams and physical properties of slags as well.

### Recovery of metal from slag

The basic slag system for FeCr production is MgO-Al<sub>2</sub>O<sub>3</sub>-SiO<sub>2</sub>-CrO<sub>x</sub>. In general, furnace atmosphere, temperature, charge (mineralogical) composition, size and type of furnace are all factors influencing the chromium loss. In general, the chromium loss from an open furnace is significant for runs of several hours duration at 1500 to 1700°C. For a closed furnace under similar conditions, however, the loss is considered to be negligible.

Among others, McCoy and Philbrook<sup>6</sup> and Maeda *et al.*<sup>18</sup> studied chromium recovery from chromium-containing slags. Chromium recovery from ferrochrome slag can reach high values of 90–99 per cent within a reasonable time. Most of the chromium left in high carbon ferrochrome slag was found to exist as undissolved chromite. Eric and Akyuzlu (1990)<sup>19</sup> investigated the slag/metal equilibrium in FeCr production conditions. They indicated that the chromium content of the slag decreases with increasing slag basicity, and this effect was stronger at relatively low basicity. The chromium content of the slag decreased rapidly as the basicity increased. The temperature and slag composition would have an effect on chromium partition. The recovery of chromium is enhanced by the presence of Al<sub>2</sub>O<sub>3</sub> in the slag. The presence of MgO leads to the formation of a spinel phase, which has a very low solubility in basic melts. The addition of MgO greatly

enhances the recovery of chromium in basic melts with a basicity ratio larger than 0.80.

It is concluded that increasing slag basicity is an effective way of reducing the loss of chromium to the slag when the basicity is relatively low. The beneficial effect levels off significantly, however, when the basicity exceeds 1.4. But adding lime has also severe drawbacks: it increases slag volume, which causes extra losses, and it raises up electrical conductivity, which can be detrimental for the furnace operation.

### Physical properties of chromium oxide containing slags

Viscosity and electrical conductivity are the physical properties with the closest relation to the practical operation of a submerged arc furnace for FeCr production. Downing and Urban<sup>20</sup> investigated the effect of chromic oxide content on the electrical conductivity of the synthetic slag containing 30 wt% Al<sub>2</sub>O<sub>3</sub>, 30 wt% MgO, 20 wt% SiO<sub>2</sub> and 20 wt% CaO, in the temperature range of 1430 to 1700°C. They concluded that Cr<sub>2</sub>O<sub>3</sub> additions increase the resistivity of the slag, i.e. decrease the electrical conductivity. Rennie *et al.*<sup>21</sup> studied effects of Cr<sub>2</sub>O<sub>3</sub>, Fe<sub>2</sub>O<sub>3</sub> and CaO on the viscosity and electrical conductivity of the FeCr slags containing 45 wt% SiO<sub>2</sub> and MgO/Al<sub>2</sub>O<sub>3</sub>=4/3 or 3/4 with melting points of 1519°C or 1554°C, respectively. Kato and Minowa<sup>22</sup> measured viscosity and electrical conductivity in the slag system of 43 mol% CaO, 43 mol% SiO<sub>2</sub>, 14 mol% Al<sub>2</sub>O<sub>3</sub> with additions of (0.68, 1.38, 2.45 mol%) Cr<sub>2</sub>O<sub>3</sub> at temperatures of 1400–1500°C. High viscosity values were obtained and the conductivity was improved by Cr<sub>2</sub>O<sub>3</sub> addition, which is an extraordinary behaviour and cannot be explained by the application of the ionic conduction.

It was concluded that additions of CaO and Fe<sub>2</sub>O<sub>3</sub> decrease the viscosity and increase the electrical conductivity of the slags. The viscosity increases with the addition of 7% Cr<sub>2</sub>O<sub>3</sub>, but decreases for higher content of 12% when the temperature is above the liquidus temperature. Cr<sub>2</sub>O<sub>3</sub> additions decrease the electrical conductivity for temperatures below the liquidus temperature, but increase for temperatures above.

Recently, Forsbacka *et al.*<sup>23</sup> measured the viscosities of the slag system of SiO<sub>2</sub>-MgO-Al<sub>2</sub>O<sub>3</sub>-CaO with the compositions near to the FeCr process in the temperature range of 1600 to 1750°C. The results were assessed by the Iida model for viscosity and gave reasonable relations in the studied composition and temperature region. The current paper by Forsbacka and Holappa presents results of viscosity measurements when CaO-SiO<sub>2</sub>-CrO<sub>x</sub> slag was in contact with metallic Cr<sup>24</sup>. The results show that addition of CrO<sub>x</sub> (with relatively high CrO fraction) decreases the viscosity, as shown in Figure 6. A similar effect is assumed in FeCr type slags, too.

Electrical conductivities of Al<sub>2</sub>O<sub>3</sub>-MgO-SiO<sub>2</sub>-Cr<sub>2</sub>O<sub>3</sub> slags have been summarized in *Slag Atlas*<sup>15</sup>. In general, electrical conductivity decreases with increasing temperature. The effect of Cr oxide seems to be complex showing a slight maximum in some of the systems discussed. The presence of two-valent CrO can further complicate the phenomenon.

In general, because of the technical difficulties in high temperature measurement and the high melting points of the

## Slags in ferroalloys production—review of present knowledge




Figure 6—The effect of  $\text{CrO}_x$  addition on the viscosity of  $\text{CaO}\cdot\text{SiO}_2$  melt (Forsbacka<sup>24</sup>)

slags, the viscosity and the electrical conductivity in the slags containing chromium oxides are not studied systematically. Further research in this field is very necessary, especially under well-controlled atmosphere due to the complex structure of chromium containing slags.

### Thermodynamic properties of manganese bearing slag

Most of the high carbon ferromanganese is produced in submerged arc furnaces. The feeding charges are manganese ores, carbonaceous reductants and fluxes (quartzite and limestone). In the upper part of the furnace, the solid state reduction occurs and the higher oxides of manganese are reduced to  $\text{MnO}$  with up-stream  $\text{CO}$  gas. The FeMn alloy and slag are formed in the high temperature bottom zone of the furnace. Depending on the type of furnace operation, the slag of a typical ferromanganese operation can either be labelled as 'high slag' or 'discard slag' operation<sup>25</sup>. 'Discard slag' practice produces slags with  $\text{MnO}$  contents around 8 to 12%. The slag is produced by silica and other basic oxides associated with the ores. The components of the slag are ca. 2 to 8%  $\text{MgO}$ , 4 to 10%  $\text{Al}_2\text{O}_3$ , ca. 35%  $\text{CaO}$  and ca. 31%  $\text{SiO}_2$ . A high basicity, i.e. high  $\text{CaO}$  and  $\text{MgO}$  contents ensure that  $\text{MnO}$  is released from the silica lattice and hence increases the recovery, which lies around 70 to 75%. In high slag practice less coke and less energy are required to produce a slag that contains more than 25%  $\text{MnO}$ . Little or no basic fluxes are added. Correspondingly, the recovery of manganese is less than for 'discard slag' practice. Typical slag analysis for the other compounds are ca. 2 to 5%  $\text{MgO}$ , 10 to 30%  $\text{Al}_2\text{O}_3$ , ca. 15%  $\text{CaO}$  and ca. 27%  $\text{SiO}_2$ . These slags are usually used in silicomanganese production, increasing

the overall manganese recovery. These silicomanganese slags form the basis for creating silicomanganese (ca. 65%  $\text{Mn}$  and ca. 15%  $\text{Si}$ ) and typically have the following composition: ca. 4%  $\text{MgO}$ , ca. 7%  $\text{Al}_2\text{O}_3$ , ca. 21%  $\text{CaO}$  and ca. 50%  $\text{SiO}_2$ .

### Manganese-oxygen system

A part of the manganese-oxygen phase diagram is shown in Figure 7<sup>26</sup>. It has similarities with the  $\text{Cr-O}$  system including several oxides manganosite ( $\text{Mn}_{1-x}\text{O}$ ), hausmanite ( $\text{Mn}_3\text{O}_4$ ), bixbyite ( $\text{Mn}_2\text{O}_3$ ) and pyrolusite ( $\text{MnO}_2$ ), depending on oxygen partial pressure and equilibrium temperature of the system. The lowest oxide  $\text{Mn}_{1-x}\text{O}$  has a very large non-stoichiometric region over which  $x$  gets values from ca. 0.11 in air to ca. 0.0004 in equilibrium with metallic  $\text{Mn}$ , corresponding to  $P_{\text{O}_2} \approx 10^{-14}$  at 1600°C<sup>26</sup>. As a consequence, manganese oxide in FeMn production conditions consists, almost completely, of  $\text{Mn}^{2+}$  and only of a minute fraction of  $\text{Mn}^{3+}$ . This is a clear difference from  $\text{CrO}_x$  containing slags in which both two and three valent forms are abundantly present in slags in FeCr process conditions.

### Activities of manganese oxides in slag

Activities of  $\text{MnO}$  in slags have been studied since the 1950s by e.g. Turkdogan and Pearson<sup>27</sup>, Abraham *et al.*<sup>28</sup>, and Rankin and See<sup>29</sup>. The data for the  $\text{CaO-SiO}_2\text{-MnO}$  system published in *Slag Atlas*<sup>15</sup> is from Abraham *et al.*<sup>28</sup>. Activity data for FeMn slags were modelled by applying neural nets by Cengizler *et al.*<sup>30</sup> at 1500°C for slag compositions lying in the range of  $\text{MnO}$  5–40%,  $\text{CaO}$  4–35%,  $\text{MgO}$  0.3–38%,  $\text{SiO}_2$  25–60% and  $\text{Al}_2\text{O}_3$  2.5–7%. In general it can be concluded that the activity coefficient of  $\text{MnO}$  in the liquid slag region varies on both sides of unity. In acid slags  $\gamma_{\text{MnO}} < 1$ , whereas in basic slags  $\gamma_{\text{MnO}} > 1$ . It also increases with increasing  $\text{MnO}$  content.

### Phase diagrams of manganese containing oxide systems

Phase diagrams of manganese containing oxide systems have been much studied since, early sixties. The binary  $\text{MnO}_x\text{-SiO}_2$




Figure 7—Assessed  $\text{Mn-O}$  system (Grundy *et al.*<sup>26</sup>)

## Slags in ferroalloys production—review of present knowledge

system was studied by Glasser<sup>31</sup> at low oxygen partial pressure from  $10^{-10}$  atm at  $1130^{\circ}\text{C}$  to  $10^{-6}$  atm at  $1555^{\circ}\text{C}$ , and by Muan<sup>32</sup> in air. The phase diagrams of the  $\text{CaO-MnO}_x\text{-SiO}_2$  system at low oxygen partial pressure were investigated by Glasser<sup>33,34</sup>. The oxygen potential of  $10^{-6}$  atm was used to control the manganese in divalent state. The low melting 'valley' ( $1600^{\circ}\text{C}$  liquidus) goes roughly from 67–43 wt%  $\text{SiO}_2$  in the  $\text{CaO-SiO}_2$  binary to 52–19 wt%  $\text{SiO}_2$  in the  $\text{MnO-SiO}_2$  binary. Replacement of  $\text{MgO}$  for  $\text{CaO}$  results in higher liquidus temperature and a narrower low melting area in the  $\text{MgO-MnO}_x\text{-SiO}_2$  system<sup>34</sup>. Recently, Roghani *et al.*<sup>35</sup> made a quite comprehensive investigation on phase equilibria in the ' $\text{MnO}$ '- $\text{CaO}$ - $(\text{Al}_2\text{O}_3 + \text{SiO}_2)$  system by equilibrating slags with  $\text{Mn-Si}$  alloy at  $1100$  to  $1550^{\circ}\text{C}$ . An example diagram is shown in Figure 8. Typical slags in manganese alloy production are in the region of triple valley point upwards from 'Galaxite'.

A quinary system consisting of all major components in the slags for ferromanganese production was studied by Eric *et al.*<sup>36</sup> and Reuter *et al.*<sup>37</sup>. The slag compositions ranged from 5–30%  $\text{MnO}$ , 20–35%  $\text{CaO}$ , 5–15%  $\text{MgO}$ , 27–58%  $\text{SiO}_2$ , 5%  $\text{Al}_2\text{O}_3$ . It is clear that liquidus temperatures vary from  $1300$  to  $1380^{\circ}\text{C}$ . The results of neural net functions also demonstrate that liquidus temperatures increase with increasing basicity. Further,  $\text{MnO}$  additions first decrease the liquidus temperature and then increase it, forming valleys in three dimensional plots. In general the slag basicity ratio has a moderate positive effect on the liquidus temperature for the slags with up to 25%  $\text{MnO}$ . For the slags containing 30%  $\text{MnO}$ , this effect is more significant. The variation of the liquidus temperature with  $\text{CaO/MgO}$  ratio depends to a large extent on the basicity and  $\text{MnO}$  content.

### Recovery of metal from slag

Rankin<sup>38</sup> and Swinbourne *et al.*<sup>39</sup> investigated the equilibrium  $\text{MnO}$  content in ferromanganese and silicomanganese slags, respectively. They concluded that the distribution of  $\text{Mn}$  and  $\text{Si}$  decreased as the alumina content increased up to 20%. Olsen and his group<sup>40</sup> have carried out a comprehensive study on the equilibrium content of  $\text{MnO}$  in the high carbon  $\text{FeMn}$  process. The slags contained  $\text{MnO}$ ,  $\text{CaO}$ ,  $\text{MgO}$ ,  $\text{SiO}_2$  and  $\text{Al}_2\text{O}_3$ . The  $\text{Al}_2\text{O}_3/\text{SiO}_2$  ratio was between 0.22–0.30. The effect of basicity and temperature on  $\text{MnO}$  content in slag in equilibrium with ferromanganese with 10 per cent  $\text{Fe}$  is shown in Figure 9.

### Physical properties of manganese oxide containing slag

Viscosities of several slags (from binary to quinary) containing  $\text{MnO}$  have been presented in *Slag Atlas*<sup>15</sup>. Eric *et al.*<sup>36</sup> measured electrical conductivity of synthetic ferromanganese slags at  $1425$ – $1430^{\circ}\text{C}$ . The slag compositions are in the range of:  $\text{MnO}$  5–30%,  $\text{CaO}$  20–35%,  $\text{MgO}$  5–15%,  $\text{SiO}_2$  27–58% and  $\text{Al}_2\text{O}_3$  5%. Reuter *et al.*<sup>37</sup> modelled the slag system by neural nets. Recently, Seetharaman, Du and co-authors<sup>41,42</sup> have measured viscosities of various slag systems, including the  $\text{CaO-SiO}_2\text{-MnO}$  system. In most cases,  $\text{MnO}$  in slags seems to slightly decrease viscosity, acting as a basic, non-bridging oxide.

### Applications in ferroalloy production

The main feature of the reaction process for  $\text{FeCr}$  production is schematically illustrated in Figure 10. As the raw material,




Figure 8— Liquidus lines for  $\text{CaO-Al}_2\text{O}_3\text{-SiO}_2\text{-MnO}$  system in equilibrium with  $\text{Mn/Si}$  alloy (redrawn from Roghani *et al.*<sup>35</sup>)

## Slags in ferroalloys production—review of present knowledge




Figure 9—MnO content in multicomponent slags in equilibrium with FeMn alloys with 10 per cent iron<sup>40</sup>




Figure 10—A schematic reaction diagram in submerged arc furnace for chromite smelting

natural chromite ore can be described with the following compounds:  $\text{Fe}_3\text{O}_4$ , iron chromite  $\text{FeO}\cdot\text{Cr}_2\text{O}_3$ , picrochromite  $\text{MgO}\cdot\text{Cr}_2\text{O}_3$ ,  $\text{MgO}\cdot\text{Al}_2\text{O}_3$  pseudo-ternary spinel solid solutions coexisting with  $(\text{Cr},\text{Al})_2\text{O}_3$ . These compounds form a complicated spinel structural solid solution. Among these components, magnetite  $\text{Fe}_3\text{O}_4$  can be easily reduced in the process, for example, by carbon. Normally the reduction takes place in stages: solid state reduction of chromite by coke and CO; chromite dissolution in the slag; reduction of chromium oxides in the slag by solid carbon, and by carbon dissolved in the metal. According to the information in the phase diagrams, minimizing the  $\text{MgO}/\text{CaO}$  ratio in the slag will improve dissolution of chromite spinel, enable more complete chromium reduction, and further result in an improved chromium recovery. On the other hand, by lowering slag basicity in the furnace, spinel dissolution and chromium recovery will also be enhanced. The most important factors in FeMn slags are the MnO content and the basicity ratio. A rather large range in the variation of furnace

power may be expected with the change of the basicity ratio at MnO contents between 5% and 10%. As the MnO content of the slag increases in the range of 20–25% MnO, the variation in basicity ratio will have very little effect on the slag resistivity. Therefore the aimed power input could only be achieved by a substantial increase in the furnace current to maintain an economical smelting rate<sup>25</sup>.

From a thermodynamic standpoint, the equilibrium between slag and metal controls the metal recovery in the process. Thermodynamic activity data of chromium oxides or manganese oxide in the slags will provide very important information to evaluate the equilibrium distribution. Maximum metal recovery could be achieved by optimized slag composition. Phase diagrams help to establish liquidus temperature of the slag, which determines the overall operating temperature and degree of overheat to the melt. The lower liquidus slag temperatures would need less power input. Based on the present study, the liquidus temperatures of FeCr slags may vary from 1550 to 1700°C, depending on

# Slags in ferroalloys production—review of present knowledge

the composition. With increasing chromium oxides content in the slag, the liquidus temperature will be raised significantly. As regards turbulence, both in the furnace and during the tapping, small droplets of metal may entrap in the slag; high slag viscosity reduces the rate of this physical separation. An excessively viscous slag may produce operational difficulties during tapping, and even cause foaming in the furnace. From the view point of reaction kinetics, low viscosity would favour diffusion processes in the slag/metal interface reaction and allow the reaction to reach equilibrium rapidly. For FeMn production, the slags with 10 to 25% MnO and basicity from 0.55 to 1.1 are of low liquidus temperatures between 1310 and 1350°C. When the slags contain more than 25% MnO and have a basicity higher than 1.4, the liquidus temperature is increased. At low MnO and low SiO<sub>2</sub> region, the slag has a relative high liquidus temperature.

Electrical conductivity of the slag assists in determining electrode penetration and power input to the furnace. Normally more resistive slag allows deeper penetration, higher voltage operation and higher power inputs. Energy generation by electric resistance heating is controlled by the secondary voltage and the electrical resistivity of burden and slag. The electrical resistivity of the burden is determined mainly by the thickness of the coke layer and type and size of the carbon reductant, i.e. low resistivity coke and high resistivity coal. The electrical resistivity of the slag will be determined by its composition. The FeCr and FeMn processes contain ore, flux additives, reducing agent, slag and metal alloy. Even though the carbon reducing agent is expected to supply the major part of the electrical current, the slag may still contribute considerably to the overall resistivity at the electrode-tip area. However, in the process the relative importance of the electrical conductivity of the slag is still in question.

## Summary and conclusions

The fundamental knowledge of chromium and manganese bearing slags was reviewed and discussed, including the oxidation state of chromium and manganese, the activities of oxides, the phase diagrams, and the factors affecting the metal recovery from slags. The physical properties such as liquidus temperature, viscosity and electrical conductivity in the related slag systems and their industrial applications were discussed.

It can be concluded that under reducing conditions of FeCr and FeMn productions, divalent and trivalent chromium and manganese are the major existing forms. In FeCr production Cr<sup>2+</sup> and Cr<sup>3+</sup> coexist in the slags; however, only Mn<sup>2+</sup> is present in the FeMn slags. Increasing slag basicity and Al<sub>2</sub>O<sub>3</sub> content have a positive effect on the activities of both CrO<sub>x</sub> and MnO<sub>x</sub> in the slags. The fraction of divalent chromium increases with increasing temperature, lowering oxygen potential and decreasing slag basicity. The activities of CrO and CrO<sub>1.5</sub> have a positive deviation from the ideal solution. Activity of MnO has both a positive and negative deviation from the ideal solution. In FeCr production, the addition of MgO into the slag greatly improves the recovery of chromium with a basicity ratio higher than 0.80. The

recovery is also enhanced by the presence of Al<sub>2</sub>O<sub>3</sub> in the slag. Increasing slag basicity increases the chromium recovery from the slags, but the effect will level off when the basicity is higher than 1.4. To minimize the chromium loss in the slags, it is also important to control the slag volume in practice while decreasing the chromium oxides concentration in the slags. The most important feature of the oxide phase diagrams is that the liquidus temperatures are affected significantly by the system oxygen potential because of the possible different oxidation states of chromium and manganese. The results on the quaternary and quinary systems are still very limited, and require to be studied further, especially under controlled oxygen partial pressures. Except for the thermodynamic properties, the effect of slag composition on physical properties must be considered in order to obtain an efficient process operation and furnace control.

## References

1. FENTON, M.D. Ferroalloys. *Minerals Yearbook, vol. 1—Metals and Minerals*, 2001
2. LUOMA, R. A Thermodynamic Analysis of the System Fe-Cr-Ni-C-O, Dr. Tech. Thesis. Acta Polytechnica Scandinavica, ch.292, Helsinki University of Technology, 2002.
3. XIAO, Y. Thermodynamic study on CrO<sub>x</sub> containing slag, Dr. Tech. Thesis, Acta Polytechnica Scandinavica, ch.210, 1993.
4. XIAO, Y. and HOLAPPA, L. Thermodynamics of slag containing chromium oxides. *INFACON 7 Conference Proceedings*, Tuset, J. Kr., Tveit, H. and Page, I.G. (eds.), Trodheim, Norway, June, 1995, pp. 319–328.
5. XIAO, Y., HOLAPPA, L., and REUTER, M.A. Oxidation State and Activities of Chromium Oxides in CaO-SiO<sub>2</sub>-CrO<sub>x</sub> Slag System. *Metallurgical and Materials Transactions B*, vol. 2, August 2002, pp. 595–603.
6. MCCOY, C.W. and PHILBROOK, W.O. The behaviour of chromium in slag-metal systems under reducing conditions. *Trans. of the Metallurgical Society of AIME*, April, 1958, pp. 226–235.
7. FROHBERG, M.G., RICHTER, K.E., and BRADATSCH, R. Die Bestimmung von zwei- neben dreiwertigem Chrom in eisenfreien Schlacken. *Arch. Eisenhüttenwesen*, vol. 38, 1967, pp. 773–774
8. MORITA, K., INOUE, A., TAKAYAMA, N., and SANO, N. The solubility of MgO·Cr<sub>2</sub>O<sub>3</sub> in MgO-Al<sub>2</sub>O<sub>3</sub>-SiO<sub>2</sub>-CaO slag at 1600°C under reducing conditions. *Tetsu-to-Hagane*, vol. 74, no. 6, 1988, pp. 999–1005.
9. PRETORIUS, E.B., SNELGROVE, R., and MUAN, A. Oxidation state of chromium in CaO-Al<sub>2</sub>O<sub>3</sub>-CrO<sub>x</sub>-SiO<sub>2</sub> melts under strongly reducing conditions at 1500°C. *J. Am. Ceram. Soc.*, vol. 75, no. 6, 1992, pp. 1378–1381.
10. PEI, W. and WJJK, O. Experimental study on the activity of chromium oxide in the CaO-SiO<sub>2</sub>-Al<sub>2</sub>O<sub>3</sub>-MgO<sub>sat</sub>-CrO<sub>x</sub> slag. *Scand. J. Metallurgy*, vol. 23, 1994, pp. 228–235.
11. MORITA, K., MORI, M., GUO, M., IKAGAWA, T., and SANO, N. Activity of chromium oxide and phase relations for the CaO-SiO<sub>2</sub>-CrO<sub>x</sub> system at 1873 K under moderately reducing conditions. *Steel Research* 70, 1999, No. 8 and 9, pp. 319–324.
12. PRETORIUS, E.B. and MUAN, A. Activity-composition relations of chromium oxide in silicate melts at 1500°C under strongly reducing conditions. *J. Am. Ceram. Soc.*, vol. 75, no. 6, 1992, pp. 1364–1377.
13. MUAN, A. Slag-metal equilibria involving chromium as a component.

## Slags in ferroalloys production—review of present knowledge

- Proceedings of MINTEK 50, Int'l Conference on Mineral Science and Technology*, L.F. Haughton (ed.), Sandton, S. Africa, 1985, pp. 897–904.
14. VAN WIJNGAARDEN, M.J.U.T. The development of an electrochemical technique for the determination of chromium oxide activities in molten slag systems. *MINTEK Report*, No. M365, council for Mineral Technology, Randburg, 20th Dec., 1988.
  15. *Slag Atlas*, 2nd edition by Verein Deutscher Eisenhüttenleute, Verlag Stahleisen GmbH, Germany, 1995.
  16. JACOB, K.T., PETRIC, A., KALE, G.M., AND IVENGAR, G.N.K. Phase relations between  $\text{Al}_2\text{O}_3\text{-Cr}_2\text{O}_3$  and  $\text{FeAl}_2\text{O}_4\text{-FeCr}_2\text{O}_4$  solid solutions at 1823K. *Ceram. Int.*, vol. 13, no. 2, 1987, pp. 123–129
  17. EL-SHAHAT, R.M. and WHITE, J. Phase equilibrium relationships in spinel-silicate systems. III. The ternary systems  $\text{MgAl}_2\text{O}_4\text{-MgFe}_2\text{O}_4\text{-Ca}_2\text{SiO}_4$  and the quaternary system  $\text{MgAl}_2\text{O}_4\text{-MgFe}_2\text{O}_4\text{-MgCr}_2\text{O}_4\text{-Ca}_2\text{SiO}_4$ . IV. The pseudoternary system  $\text{MgAl}_2\text{O}_4\text{-MgCr}_2\text{O}_4\text{-Ca}_3\text{MgSi}_2\text{O}_8$ . *Trans. Br. Ceram. Soc.*, vol. 65, no. 9, 1966, pp. 497–519.
  18. MAEDA, M. and SANO, N. Thermodynamics of chromium oxide in molten  $\text{CaO-MgO-Al}_2\text{O}_3\text{-SiO}_2$  slag coexisting with solid carbon. *Tetsu-to-Hagane*, vol. 68, no. 7, 1982, pp. 759–766.
  19. ERIC, R.H. and AKYUZLU, M. Slag-metal equilibria in the system Fe-Cr-Si-Ca-Mg-Al-O. *MINTEK Report* No. M405, August, 1990.
  20. DOWNING, J.H. and URBAN, L. Electrical conduction in submerged arc furnaces. *J. of Metals*, March, 1966, pp. 337–344.
  21. RENNIE, M.S., HOWAT, D.D., and JOCHENS, P.R. The effects of chromium oxide, iron oxide and calcium oxide on the liquidus temperatures, viscosities and electrical conductivities of slags in the system  $\text{MgO-Al}_2\text{O}_3\text{-SiO}_2$ . *J. South Afr. Inst. Min. Metall.*, 1972, pp. 1–9.
  22. KATO, M. and MINOWA, S. Viscosity measurements of molten slag,—properties of slag at elevated temperature (part I). *Transactions ISIJ*, vol. 9, 1969, pp. 31–38.
  23. FORSBACKA, L., HOLAPPA, L., IIDA, T., KITA, Y., and TODA, Y. Experimental study of viscosities of selected  $\text{CaO-MgO-Al}_2\text{O}_3\text{-SiO}_2$  slags and application of the Iida model. *Scandinavian Journal of Metallurgy*, vol. 32, 2003, pp. 273–280.
  24. FORSBACKA, L. and HOLAPPA, L. Viscosity of  $\text{SiO}_2\text{-CaO-CrO}_x$  slags in contact with metallic chromium and application of the Iida model. *7th International Conference on Molten Slags, Fluxes and Salts*. Cape Town, South Africa January 2004, pp. 129–136.
  25. REUTER, M.A. and XIAO, Y. Slag properties and chemistry in ferroalloy production and practical implications, *Schlacken in der Metallurgie*, Vorträge beim 35. *Metallurgischen Seminar, des Fachausschusses für Metallurgische Aus- und Weiterbildung der GDMB* vom 17. bis 19. März 1999 in Aachen, Germany, pp. 95–140.
  26. GRUNDY, A.N., HALLSTEDT, B., GAUCKLER, and L.J. Assessment of the Mn-O System. *Journal of Phase Equilibria*, vol. 24, no. 1, 2003, pp. 21–38.
  27. TURKDOGAN, E.T. and PEARSON, J. Activities of constituents of Iron and Steelmaking Slags. *Transactions of the Metallurgical Society of AIME*. vol. 212, 1958, pp. 890–892.
  28. ABRAHAM, P.P., DAVIES, M.W., and RICHARDSON, F.D. Activities of Manganese Oxide in Silicate and Aluminate Melts, *JISI*, vol. 196, 1960, pp. 82–89.
  29. RANKIN, W.J. and SEE, J.B. The Slag-Metal Equilibrium and the Activities of Slag and Metal Components in the Production of High Carbon Ferromanganese. *National Institute for Metallurgy Report*, no. 1959, Randburg, South Africa, 1978
  30. CENGIZLER, H., ERIC, R.H., and REUTER, M.A. Modelling of the activities and activity coefficients of Mn in ferromanganese slags. *Proceedings 5th International Conference on Molten Slags, Fluxes and Salts '97, Australia*, Iron and Steel Society, Warrendale, PA, 1997, pp. 75–90.
  31. GLASSER, F.P. The system  $\text{MnO-SiO}_2$ . *Am. J. Sci.*, vol. 256, no. 6, 1958, pp. 398–412.
  32. MUAN, A. Phase equilibria in the system manganese oxide — $\text{SiO}_2$  in air. *Am. J. Sci.*, vol. 257, 1959, pp. 297–315.
  33. GLASSER, F.P. The system  $\text{Ca}_2\text{SiO}_4\text{-Mn}_2\text{SiO}_4$ . *Am. J. Sci.*, vol. 259, no. 1, 1961, pp. 46–59.
  34. GLASSER, F.P. The ternary system  $\text{CaO-MnO-SiO}_2$ . *J. Am. Ceram. Soc.*, vol. 45, no. 5, 1962, pp. 242–249.
  35. ROGHANI, G., JAK, E., and HAYES, P. Phase-Equilibrium Data and Liquidus for the System ' $\text{MnO}$ '- $\text{CaO-Al}_2\text{O}_3\text{-SiO}_2$  at  $\text{Al}_2\text{O}_3/\text{SiO}_2$  of 0.55 and 0.65. *Metallurgical and Materials Transactions B*, vol. 34B, April 2003, pp.173–182.
  36. ERIC, R.H., HEJJA, A.A., and STANGE, W. Liquidus temperature and electrical conductivities of synthetic ferromanganese slags. *Minerals Engineering*, vol. 4, no. 12, 1991, pp. 1315–1332.
  37. REUTER, M.A., ERIC, R.H., and HEJJA, A.A. Modelling of liquidus temperature and electrical conductivities of synthetic ferromanganese slags by the use of neural nets. *Proceedings of Sensors and Modelling in the Materials Processing: Techniques and Applications*, Viswanathan, R.G. Reddy, and J.C. Malas), (eds.) The Minerals, Metals and Materials Society, Orlando, USA, 1997, pp. 35–53
  38. RANKIN, W. J. Si-Mn equilibrium in ferromanganese alloy production. *Section C of the Transactions of the Institution of Mining and Metallurgy*, vol. 88, 1979, pp. C167–C174.
  39. SWINBOURNE, D.R., RANKIN, W.J., and ERIC, R.H. The effect of alumina in slag on manganese and silicon distribution in silicomanganese smelting, *Metallurgical Transactions B*, vol. 26B, February 1995, pp. 59–65.
  40. OLSEN, S.E. The slag basicity concept in the HC FeMn process. *INFACON 9 Conference Proceedings*, The Ferroalloys Association, Washington DC; Quebec City, Canada, June 3–6, 2001, pp. 280–285.
  41. SEETHARAMAN, S., SICHEN, DU, and JI, F.-Z. Estimation of Viscosities of Ternary Silicate Melts using the Excess Gibbs Energy of Mixing. *Metallurgical and Materials Transactions B*, vol. 31B, February 2000, pp. 105–109.
  42. JI, F.-Z. Experimental Studies of the viscosities in  $\text{CaO-MnO-SiO}_2$  and  $\text{CaO-FeO-MnO-SiO}_2$  Slags. *Metallurgical and Materials Transactions B*, vol. 32B, February 2001, pp. 181–186. ◆

# Zircon prices continue to rise as demand exceeds supply

## New report analyses zirconium supply and demand worldwide

There is a very real risk that demand for zircon could soon be substantially greater than global supply. In a new report from market analyst Roskill it has been forecast that the shortfall could be more than 100 000 t in 2005. Some industry observers believe that, even if the planned mineral sands projects come into production over the next 10 years, demand will still outstrip supply.

However, *The Economics of Zirconium* (11th Edition, 2004) explains that the shortage of zircon is not a reflection of the mineral's availability—mineable reserves are sufficient to sustain current levels of output for over 30 years—but is largely a result of mineral sands production. Zircon is extracted as a co-product or by-product of titanium minerals, the market for which is over supplied. Global demand for TiO<sub>2</sub> feedstock thus has a major effect on both the production of zircon and the viability of new mining projects.

### *Threat of substitution of zircon with alternative materials*

If zircon production does not increase to meet the expanding demand, prices will continue to rise to a point where consumers in one or more industries may switch to using alternative materials. Such a shift has taken place before. In the mid-1980s raw material shortages and spiralling prices led manufacturers of refractories in Japan to substitute alumina spinel for zircon in many applications. The result was a sharp decline in demand for zircon in refractories, which has never been reversed.

In the ceramics industry zircon is generally regarded as having no substitute as an opacifier. Should the price continue to rise, however, zircon millers will have little choice but to pass on the increases they have so far been absorbing and ceramics manufacturers will come under strong pressure to find alternatives.

### *South Africa emerges as major producer*

The last three decades have seen a major shift in the global distribution of zircon production. In the 1970s Australia accounted for at least 50% of total output and the USA some 20-30%, while South Africa was only a very minor producer. The development of the Richards Bay beach sands operation in the late 1970s made South Africa the second largest zircon producer worldwide, reducing Australia's dominance. Today, South Africa and Australia produce approximately the same amount of

zircon and account for 80% of total supply, with the USA providing much of the rest.

### *Four corporate groups dominate supply*

In 2001 the twelve largest producers had a combined output of just over 1 Mt, about 80% of the world total. Production is now dominated by four corporate groups: Iluka Resources, with outright ownership of, or controlling interests in operations in Australia and the USA; Rio Tinto and BHP Billiton, who jointly own Richards Bay Minerals in South Africa; and Anglo American, which owns Namakwa Sands in South Africa and ultimately controls the Titor operations in both South Africa and Australia. These four companies effectively control about three quarters of the world's zircon supply.

### *China increasing competition in ceramics industry*

World consumption of zircon was about 1 Mt in 2003 (excluding FSU). With a share of 35%, Europe has long been the principle consuming region, largely a reflection of the sizeable Spanish, Italian and Turkish ceramics industries. That position will be challenged in the future by the strong growth in demand taking place in China, much of it from the rapidly expanding ceramics industry, with China's output of tiles growing by over 20% in 2002.

### *Restricted supply causes sustained price rise*

Prices for zircon sand have been rising since 1999. Since the beginning of 2003, ceramic grade zircon sand prices have increased by nearly 25% from US\$370-400/t to US\$450-500/t in June 2003, reflecting tight supply. Over the same period the price for opacifier-grade milled zircon has increased from US\$600-620/t to US\$680-720/t, a rather lower rate of increase. This indicates the strong competition between zircon milling companies in the west and their need to remain competitive in an industry facing a strong challenge from China.

*The Economics of Zirconium* is available at £1950/US\$3900/EUR3415 from Roskill Information Services Ltd, 27a Leopold Road, London SW19 7BB, England. Tel: +44 20 8944 0066 Fax: +44 20 8947 9568 · E-mail: info@roskill.co.uk ◆